



COPY OF PAPERS
ORIGINALLY FILED

RESPONSE UNDER 37 CFR 1.116
EXPEDITED PROCEDURE
EXAMINING GROUP 1711

PATENT
Attorney Docket No. 203924

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Application of:

Kodama et al.

Application No. 09/502,834

Filed: February 11, 2000

For: POLYBENZAZOLE ARTICLE
AND PRODUCTION METHOD
THEREOF

Art Unit: 1711

Examiner: D. Truong

RECEIVED
JUL 29 2002
TC 1700

**PENDING CLAIMS AFTER AMENDMENTS MADE IN
RESPONSE TO OFFICE ACTION DATED FEBRUARY 20, 2002**

1. A polybenzazole article superior in light resistance, which comprises a polybenzazole and a light-resisting agent that allows for a regular reflectance of the article of not more than 30% in not less than 30% of the wavelength region of from 450 nm to 700 nm, wherein the light-resisting agent is at least one member selected from the group consisting of aniline, *o*-phenylenediamine, *m*-phenylenediamine, *p*-phenylenediamine, *o*-aminophenol, *m*-aminophenol, *p*-aminophenol, 2-amino-4-nitrophenol, 2-amino-4-sulfonamide, and 1,8-diaminonaphthalene.

2. The polybenzazole article of claim 1, wherein the light-resisting agent allows for a regular reflectance of the article of not more than 20% in not less than 10% of the wavelength region of from 450 nm to 700 nm.

3. The polybenzazole article of claim 1, which has a strength of not less than 35 g/d.

6. The polybenzazole article of claim 1, wherein the light-resisting agent is contained in a proportion of 0.01 to 20% by weight of the article.